



CENTRO SERVIZI TESSILI s.r.l.
Laboratorio analisi chimiche e prove fisiche
TEXDECOR CASAMANCE

FABRIC TEST
 Lab. ref. N° 26911

Date received: 04/07/22
 Date issued: 07/07/22
 Article: FLORA
 Col.: BLU

FLAMMABILITY TEST	RESULT	TESTING METHODS
Reaction to fire by applying of small flame	Pretreatment : none Flame application : 12 s Post combustion time : 10 s (Level 1) Smouldering time : 6 s (Level 1) Damage : < 150 mm (Level 1) Dripping : yes, burning time > 0 s (Level 1) Class I	UNI 8456 : 2010

Tecnico di laboratorio
 Cristiano Benigni

Responsabile di laboratorio
 Dott. Simone Calamai



Via 5 giornate di Milano n°24
 Tel. +39 0574 622887 fax +39 0574 1660601

59100 PRATO
 e-mail: centroservizitessili@libero.it