



**Texdecor - Casamance**  
**2, rue d'Hem**  
**59780 WILLEMS**  
**France**

**Your notice of**  
26-09-2023

**Your reference**

**Date**  
09-10-2023

## Analysis Report 23.05110.12

Required tests :

**UK Furniture and Furnishings  
(Fire) (Safety) regulations (1988)  
No. 1324**

**UK Furniture and Furnishings  
(Fire) (Safety) regulations (1988)  
No. 1324**

**The Furniture and Furnishings (Fire) (Safety) regulations :  
1988 No. 1324 - Schedule 4 part I – The cigarette test - BS 5852  
part 1 (1979)**

**The Furniture and Furnishings (Fire) (Safety) regulations :  
1988 No. 1324 - Schedule 5 part I – The match test - BS 5852  
part 1 (1979)**

Sample id	Information given by the client	Date of receipt
T2321868	M411	26-09-2023


Gina Créelle  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**Samples**

T2321868  
M411





**Reference:** T2321868 - M411

**The Furniture and Furnishings (Fire) (Safety) regulations : 1988 No. 1324 - Schedule 4 part I – The cigarette test - BS 5852 part 1 (1979)**

Date of ending the test 09-10-2023  
Standard used UK Furniture and Furnishings (Fire) (Safety) regulations (1988) No. 1324  
Deviation from the standard -  
Conditioning 23°C, relative humidity 50%  
Based on information given by the client: specimens have not been cleaned  
Filling T 23140 (Recticel) \* - non-fire retardant foam - ± 22 kg/m<sup>3</sup>  
\* The filling complies with the requirements as indicated in schedule 5 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

	1	2
<b>Smouldering criteria</b>		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
<b>Flaming criteria</b>		
Occurrence of flames	no	no
	non-ignition	non-ignition

**Conclusion Pass**

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

**Reference:** T2321868 - M411

**The Furniture and Furnishings (Fire) (Safety) regulations : 1988 No. 1324 - Schedule 5 part I – The match test - BS 5852 part 1 (1979)**

Date of ending the test 09-10-2023  
Standard used UK Furniture and Furnishings (Fire) (Safety) regulations (1988) No. 1324  
Deviation from the standard -  
Conditioning 23°C, relative humidity 50%  
Based on information given by the client: specimens have not been cleaned  
Filling T 23140 (Recticel) \* - non-fire retardant foam -  $\pm 22 \text{ kg/m}^3$   
\* The filling complies with the requirements as indicated in schedule 5 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988  
Flame application time (s) 20

	1	2
<b>Smouldering criteria</b>		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 15 min	no	no
Final examination / active smouldering	no	no
<b>Flaming criteria</b>		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
	non-ignition	non-ignition

**Conclusion Pass**

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.