



**Texdecor - Casamance**  
**2, rue d'Hem**  
**59780 WILLEMS**  
**France**

**Your notice of**  
13-04-2022

**Your reference**

**Date**  
22-04-2022

## Analysis Report 22.02056.02

Required tests :

**BS 5867-2 (2008)**

| Sample id | Information given by the client | Date of receipt |
|-----------|---------------------------------|-----------------|
| T2207362  | 3271                            | 13-04-2022      |

Gina Créelle  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T2207362 - 3271**

**Determination of the flammability of textile fabrics for curtains and drapes**

Date of ending the test 19-04-2022  
Standard used EN ISO 15025 (2002)  
Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Information given by the client Face A = face B

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 15

|                         | Length |    |    | Width |    |    |
|-------------------------|--------|----|----|-------|----|----|
|                         | 1      | 2  | 3  | 1     | 2  | 3  |
| Flame or hole on edge   | no     | no | no | no    | no | no |
| Flaming debris droplets | no     | no | no | no    | no | no |

**Type B performance requirements**

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris droplets

**Conclusion** Flammability, of the uncleaned fabric, complies with the requirements of BS 5867-2:2008, type “B”