



Texdecor - Casamance
2, rue d'Hem
59780 WILLEMS
France

Your notice of
21-02-2023

Your reference

Date
10-03-2023

Analysis Report 23.00975.20

Required tests :

BS 5867-2 (2008)

Sample id	Information given by the client	Date of receipt
T2304122	4617	21-02-2023

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2304122 - 4617

Determination of the flammability of textile fabrics for curtains and drapes

Date of ending the test 06-03-2023
Standard used EN ISO 15025 (2002)
Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%
Room 21°C, relative humidity 32%

Information given by the client Front ≠ back

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.


Flame application time (s) 15

Tested side Front

	Length			Width		
	1	2	3	1	2	3
Flame or hole on edge	yes	no	no	no	no	no
Flaming debris droplets	no	no	no	no	no	no

Tested side Back

	Length			Width		
	1	2	3	1	2	3
Flame or hole on edge	no	no	no	no	no	no
Flaming debris droplets	no	no	no	no	no	no



Additional tests

Tested side

Front

	Length			Width		
	1	2	3	1	2	3
Flame or hole on edge	no	no	no	no	no	no
Flaming debris droplets	no	no	no	no	no	no

Type B performance requirements

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris droplets

Conclusion

Flammability, of the uncleaned fabric, complies with the requirements of BS 5867-2:2008, type "B"