



**Texdecor - Casamance**  
**2, rue d'Hem**  
**59780 WILLEMS**  
**France**

**Your notice of**  
29-09-2021

**Your reference**

**Date**  
05-10-2021

## Analysis Report 21.06077.02

Required tests :

**BS 5867-2 (2008)**

Sample id	Information given by the client	Date of receipt
T2120875	M317	29-09-2021

**Gina Créelle**  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference:** T2120875 - M317

**Determination of the flammability of textile fabrics for curtains and drapes**

Date of ending the test 05-10-2021  
Standard used EN ISO 15025 (2002)  
Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Information given by the client Face A ≠ face B

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 15

Tested side Face A

	Length			Width		
	1	2	3	1	2	3
Flame or hole on edge	no	no	no	no	no	no
Flaming debris droplets	no	no	no	no	no	no

Tested side Face B

	Length			Width		
	1	2	3	1	2	3
Flame or hole on edge	no	no	no	no	no	no
Flaming debris droplets	no	no	no	no	no	no

**Type B performance requirements**

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris droplets

**Conclusion** Flammability, of the uncleaned fabric, complies with the requirements of BS 5867-2:2008, type “B”