



Texdecor - Casamance
2, rue d'Hem
59780 WILLEMS
France

Your notice of
21-02-2023

Your reference

Date
09-03-2023

Analysis Report 23.00975.06

Required tests :
BS 5852 (2006)

**Clause 11 (upholstery composite) - Assessment of the
ignitability of upholstered seating - crib ignition source no. 5**

Sample id	Information given by the client	Date of receipt
T2304121	4646	21-02-2023

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2304121 - 4646

Clause 11 (upholstery composite) - Assessment of the ignitability of upholstered seating - crib ignition source no. 5

Date of ending the test 03-03-2023
Standard used BS 5852 (2006)
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Based on information given by the client: specimens have not been cleaned

Filling C55120 (Recticel) * - fire retardant foam - ± 60 kg/m³

* The filling complies with schedule 1 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smoulders more than 100 mm from source	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flames to extremities	no	no
Flames through thickness	no	no
Flame time specimen >10 min	no	no
Flame time specimen	5 min 05 s	4 min 45 s
Flaming debris	no	no
	non-ignition - NI/5	non-ignition - NI/5

Conclusion Non-ignition - NI/5