



**Texdecor - Casamance**  
**2, rue d'Hem**  
**59780 WILLEMS**  
**France**

**Your notice of**  
13-01-2022

**Your reference**

**Date**  
31-01-2022

## Analysis Report 22.00253.02


Required tests :

**California Technical Bulletin 117 (2013)**

Sample id	Information given by the client	Date of receipt
T2200858	reference 3280	13-01-2022

**Gina Créelle**  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T2200858 - reference 3280**

**Section 1 : cover fabric test**

Date of ending the test 26-01-2022  
 Standard used ASTM E1353-08a (2013)  
 Product standard California Technical Bulletin 117 (2013)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Filling T 30130 (Recticel) - non-fire retardant foam  
 Cover Sheeting Material Composition 100 % cotton - laundered weight (125 ± 28) g/m<sup>2</sup>

	<b>1</b>	<b>2</b>	<b>3</b>
<b>Open flaming</b>	no	no	no
<b>Smoulders more than 45 min.</b>	no	no	no
<b>Vertical char length &gt; 45 mm</b>	no	no	no

**Test criteria**

- no open flaming
- smouldering ≤ 45 minutes
- vertical char ≤ 45 mm

**Requirements**

- all specimens meet the test criteria → PASS
- two or more specimens fail the test criteria → FAIL
- one specimen fails the test criteria → 3 additional tests → PASS
- all specimens meet the test criteria

**Conclusion Pass**