

Texdecor - Casamance 2, rue d'Hem 59780 WILLEMS France

Your notice of 21-03-2023

Your reference

Date 14-04-2023

Date of receipt

21-03-2023

Analysis Report 23.01606.02

Required tests : NFPA 260 (2013)

Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture - Cover Fabric Classification

Sample 1d	
T2306870	

Information given by the client M143

réelle

Gina Créelle Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

 $\label{eq:centre} \texttt{CENTEXBEL} \bullet \texttt{textile competence centre} \bullet \texttt{www.centexbel.be} \bullet \texttt{www.vkc.be}$

GENT • Technologiepark 70 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 29 27 00 • fax +32 56 29 27 01 • info@vkc.be VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

6



Reference: T2306870 - M143

<u>Tests and Classification System for Cigarette Ignition Resistance of Components of</u> <u>Upholstered Furniture - Cover Fabric Classification</u>

Date of ending the test Standard used	14-04-2023 NFPA 260 (2013)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Filling Cover Sheeting Material	T 23140 (Recticel) - non-fire retardant foam - \pm 22 kg/m ³ Composition 100 % cotton - laundered weight (125 \pm 28) g/m ²

	1	2	3
Ignition of the test specimen	no	no	no
Vertical char length > 45 mm	no	no	no

Cover Fabric Classification

CLASS I	- no evidence of ignition of any test assembly	
	- vertical char on any of the three specimens shall not exceed 45 mm.	
CLASS II	- cover fabrics that do not meet Class 1 criteria	

Conclusion

Class I

in

f

0)